

W.S. Tyler

Date:	January 5, 2010
Technician Name:	John Smith
Test Record Number:	zf11235
Material / Product:	Silica Sand
Shaker:	RX-29
Running Time:	15 min
Sample Size (Units):	100
Sample Size (Unit of Measure)	grams

Signature(s)

Test Sieve Analysis Results

Opening	Sieve Series USA Designation	Weight Retained on Sieve / UM	Cumulative Weight Retained
2mm	USA No. 10	1	1
300um	USA No. 50	5	6
150um	USA No. 100	45	51
106um	USA No. 140	30	81
75um	USA No. 200	15	96
45um	USA No. 325	2	98
	USA No.		
	USA No.		
	USA No.		
	USA No.		
	USA No.		
	USA No.		
	USA No.		
	Pan	2	100
Totals:		100	100

[Redacted]

[Redacted]

**Cumulative
Percent**

- 1%
- 6%
- 51%
- 81%
- 96%
- 98%

100%
100%