

Mesh	Diameter of Wire (in.)	Width of Opening		Weight Per 100 Sq. Ft.	Open Area
		Inch	Millimeter		
100	0.0045	0.0055	0.1397	16.2	30.30%
110	0.004	0.0051	0.1295	13.9	31.40%
120	0.0037	0.0046	0.1168	13	30.70%
130	0.0034	0.0043	0.1092	11.9	31.10%
140	0.0029	0.0042	0.1067	9.3	34.90%
150	0.0026	0.0041	0.1041	8	37.40%
160	0.0025	0.0038	0.0965	7.9	36.40%
170	0.0024	0.0035	0.0889	7.7	35.10%
180	0.0023	0.0033	0.0838	7.5	34.70%
200	0.0021	0.0029	0.0737	7	33.60%
220	0.0017	0.0028	0.0711	5	38.70%
240	0.0016	0.0026	0.066	4.7	38.30%
250	0.0016	0.0024	0.061	5.1	36.00%
TWILLED					
110	0.0045	0.0046	0.1168	17.2	25.60%
120	0.004	0.0043	0.1092	14.8	26.80%
130	0.0038	0.0039	0.0991	14.5	25.60%
140	0.0033	0.0038	0.0965	11.8	28.60%
150	0.003	0.0037	0.094	10.4	30.40%
160	0.0028	0.0035	0.0889	9.6	30.80%
170	0.0026	0.0033	0.0838	8.8	31.20%
180	0.0025	0.0031	0.0787	8.6	30.60%
200	0.0023	0.0027	0.0686	8.1	29.10%
230	0.0018	0.00255	0.0647	5.8	34.30%
250	0.0016	0.0024	0.061	4.9	36.00%
270	0.0016	0.0021	0.0533	5.3	32.20%
300	0.0015	0.0018	0.0457	5.2	29.70%
325	0.0014	0.0017	0.0432	4.9	30.00%
400	0.001	0.0015	0.0381	3.7	36.00%