

Mesh	Opening		Wire Diameter		Open Area
	Inch	Millimeter	Inch	Millimeter	
16	0.0535	1.359	0.009	0.229	73.30%
18	0.0466	1.184	0.009	0.229	70.20%
20	0.041	1.041	0.009	0.229	67.20%
22	0.38	0.965	0.0075	0.191	69.70%
24	0.0342	0.869	0.0075	0.191	67.20%
26	0.031	0.787	0.0075	0.191	64.80%
28	0.0282	0.716	0.0075	0.191	62.40%
30	0.0263	0.681	0.0065	0.165	64.80%
32	0.0248	0.63	0.0065	0.165	62.70%
34	0.0229	0.582	0.0065	0.165	60.70%
36	0.0213	0.541	0.0065	0.165	58.70%
38	0.198	0.503	0.0065	0.165	56.70%
40	0.0185	0.47	0.0065	0.165	54.80%
43	0.0183	0.465	0.005	0.127	61.60%
46	0.0172	0.437	0.0045	0.114	62.90%
48	0.0163	0.414	0.0045	0.114	61.50%
50	0.0155	0.394	0.0045	0.114	60.10%
54	0.0145	0.368	0.004	0.102	61.50%
56	0.0138	0.351	0.004	0.102	60.20%
58	0.0132	0.335	0.004	0.102	59.00%
60	0.0127	0.323	0.004	0.102	57.80%
62	0.0121	0.307	0.004	0.102	56.50%
66	0.0112	0.285	0.004	0.102	54.20%
70	0.0106	0.269	0.0037	0.094	54.90%
72	0.0102	0.259	0.0037	0.094	53.80%
74	0.0098	0.249	0.0037	0.094	52.70%
76	0.0095	0.241	0.0037	0.094	51.70%
78	0.0091	0.231	0.0037	0.094	50.60%
80	0.0088	0.224	0.0037	0.094	49.60%
84	0.0084	0.213	0.0035	0.089	49.80%
88	0.0079	0.201	0.0035	0.089	47.90%
94	0.0071	0.18	0.0035	0.089	45.00%
105	0.0065	0.165	0.003	0.076	46.90%
120	0.0057	0.145	0.0026	0.066	47.30%
135	0.0051	0.129	0.0023	0.058	45.00%
145	0.0047	0.119	0.0022	0.056	46.90%
165	0.0042	0.107	0.0019	0.048	47.10%
200	0.0034	0.086	0.0016	0.041	46.20%
230	0.0029	0.074	0.0014	0.036	46.00%